

Aladdin warrants, that at the time of the quality release or subsequent retest date this product conformed to the information contained in this publication. The current Specification sheet may be available at Aladdin-e.com. For further inquiries, please contact Technical Service. Purchaser must determine the suitability of the product for its particular use. See reverse side of invoice or packing slip for additional terms and conditions of sale.

Specification Sheet

Product Name: Poly(methyl methacrylate)
Specifications & Purity: High flow injection grade

SKU# **P141442**

Parameter Limit Values

Melt Flow Index 15.2-16.5 (g/10min)

Tensile Elongation 4.6-5.3 (%)

Flexural Strength 880-975 (kg/cm²)

Light Transmission 90-95 (%)

Heat deflection temperature 87-92 (°C)

Tensile strength 620-680 (kg/cm²) Vicat Softening Temp 100-105 (°C)

Izod Impact Strenght 2.0Kg-cm/cm

Aladdin warrants, that at the time of the quality release or subsequent retest date this product conformed to the information contained in this publication. The current Specification sheet may be available at Aladdin-e.com. For further inquiries, please contact Technical Service. Purchaser must determine the suitability of the product for its particular use. See reverse side of invoice or packing slip for additional terms and conditions of sale.

Phone: +86 400 620 6333 Email: Sale@aladdin-e.com Web: https://www.aladdin-e.com